

Claywood Oak



Coast Oak



Light Sand



Traditional Oak



Weathered Oak



White Dune

deZIGN
THE ART OF FLOORING

series 122.

deZIGN
THE ART OF FLOORING

series 122.

TECHNICAL SPECIFICATIONS

SUBJECT	MAIN PARAMETER	SPECS.
GENERAL INFORMATION		
Thickness	2.0 mm	
Wear Layer	Class 22+	
Packaging Unit	18 pieces/ box = 5.02m²	
Plank Size	228.6 x 1219.2 x 2 mm	
Application	General domestic	
Guarantee	10 year residential	
TECHNICAL DATA		
Name	LVT (2.0/0.2mm)	
Type of flooring	Heterogeneous PVC floor covering	ISO 10582
Classification	22+	ISO 10874
Structure	Coating, wear layer(0.2mm), print film(0.07mm)	
	Base layer (1.73mm)	
Surface treatment	Coating	
Size	Deviation ≤0.15% of nominal length up to 0.5mm maximum	ISO 24342V
Squareness, mm	≤400mm deviation≤0.25; >400mm, ≤0.35>400mm, ≤0.5	ISO 24342V
Straightness, mm	≤400mm deviation≤0.25; >400mm, ≤0.35>400mm, ≤0.5	ISO 24342V
Overall thickness, mm	Average: + 0.13/-0.10mm, individual value: average +/- 0.15mm	ISO 24346V
Wear layer thickness, mm	+13%/ -10% - not exceed ±0.1mm,	ISO 24340V
Total mass per unit	+13 %	ISO 23997V
area(average)-[g/m2]	-10 %	ISO 23997V
Dimensional stability,80 ℃×6h	Glued ≤±0.4% | Dry-joint & glued ≤±0.25% | Loose lay ≤±0.15%	ISO 23999V
Curl, 80 ℃×6h	Glued ≤±8mm | Dry-joint & glued ≤±2mm | Loose lay ≤±1mm	ISO 23999V
Residual indentation(average)	≤0.1 mm	ISO 24343-1V
Resistance to heat Color Fastness to heat	ΔE ≤8 ave., max	ASTM F1514
Resistance to light Color Fastness to light	6 minimum / Δ E ≤8 after 300 h	ISO 105-BO2:2014,
Staining and resistance to chemicals	Class 0	ISO 26987V
Reaction to fire	Bfl-s1	EN 13501-1V
TVOC	≤ 0.5 mg/m3	B standard
Slip resistance	≥R9	DIN 51130V
	DS	EN 13893V
Abrasion resistance	Group T	EN 660-2V
Toxicity	Non-toxic, no heavy metals	EN71-3V
Formaldehyde	E1	EN717-1
Use recycled materials or not	No	
Features	Easy-clean | Wood/stone look | Durable | Slip-resistant | Non-toxic	
Using area	Residential & Commercial Applications	

INSTALLATION & MAINTENANCE GUIDELINES	
INSTALLATION & MAINTENANCE GUIDELINES	Adhere to manufactures installation parameters
Installation	Non-abrasive detergent & micro fibre mop
Cleaning & Maintenance	Avoid excessive exposure to water
Caution	Do not expose to direct sunlight